

DF-550

Acryl adhesive

**DAEHEUNG CHEMICAL**

DF-550 is an acrylic resin adhesive for the use of bottom which is great in PVC carpet & tile's adhesive property and cold resistance, heat resistance. This adhesive has a LONG TACK as all round adhesive, and so it is excellent in working construction.

1. Uses

- Adhesive for the use of bottom a carpe, tile (deco tile, rex tile, sense tile, deluxe tile)

2. Characteristics

- Long tack, this adhesive is possible for one side anointment.
- An excellent in initial bonding strength property.
- Reconstruction is convenient because this adhesive is aqueous adhesive.
- Cold-resistant adhesive property is comparatively satisfactory. (until -20°C)

3. Physical properties

| Properties | Value |
|-------------------------|---|
| Main component | Acrylic resin emulsion |
| Color | Milky white emulsion |
| Solid contents | 68±2 % (at 105±5°C x 3hr) |
| Viscosity | 13,000~17,000 cps (at 20°C) |
| Specific gravity | Above 1.25 g/m ³ (at 20°C) |
| Open time | 10~120 min |
| Using time | After 24 hr |
| Hardening time | After 72 hr |
| Application temperature | 0~50 °C |
| Application quantity | 300±50 g/m ² |
| Shelf life | 9 months in unbroken package under dry and cool condition |

4. How to use

- Remove all dirt, grease, water and rust from the surface before applying.
- Spread thinly the adhesive over one of the surfaces to be bonded by using applicator.
- After application, wait for a moment (10~30 min) and bond.
- Press with roller enough.

5. Caution

- Avoid direct rays of the sun and keep in cool and dry place. (5~25℃)
- The brush and other tools for spreading the adhesive, the stain parts and hands, etc, should be cleaned by wiping or washing with water.
- Keep out of reach of children.
- Close the cap tightly after using it

6. Packaging

- 4kg, 10kg PE C/N

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

DAEHEUNG CHEMICAL CO., LTD.

(68, Sandan-ro 64beon-gil, Pyeongtaek-si,
Gyeonggido, Korea)

Telephone +82-2-554-8211, +82-31-668-1424

Facsimile +82-2-554-8215, +82-31-668-1425

Website www.dhcbond.co.kr



DAEHEUNG CHEMICAL