



HD-T is a urethane base adhesive, which is excellent bonding strength. It is good spray and roll coating type for one part moisture curing adhesive.

1. Uses

- PVC, ABS and Various plastic.
- Wood and Iron plate.
- Metal and PVC form.

2. Characteristics

- Excellent in initial bonding strength and final bonding strength.
- Excellent in cold resistance and water resistance.
- Good spray characteristic.

3. Physical properties

Properties	HD-T	Reference
Main component	Poly urethane	
Color	Dark brown transparent viscous liquid	
Solid contents	85~89 %	at 105±5℃ x 3hr
Viscosity	500~1,000 cps	at 20℃, BF #2, 50rpm
Specific gravity	1.10±0.05 g/cm ³	at 20℃
Pot life	1 hr	at 20℃
Curing time	24 hr	at 20℃
Shelf life	3months in unbroken package under dry and cool condition	

4. How to use

• Remove all dirt, grease, water and rust from the bonding surface before applying

• Coating it both surface and joint and press then tightly

- Applied amount: 100~200 g/m²

- OPEN TIME: 20~30 min

- Compression pressure : Over 3~5 kgf/cm²

- Press time: 3~6 hours

- Curing time : Over 24 hours
- Working conditions standard : Room temperature(15~25 °C), Humidity(40~60%)
- After adhesive curing and proceed to the machining process.
 - * It is difference for kind of material, kind of machine and work situation.

5. Caution

- Avoid direct rays of the sun and keep in cool(5~25℃) and dry place.
- Keep it away from the fire.
- Use the adhesive within pot-life.
- Close the cap tightly after using it.
- Ventilation the room well because of containing solvent.
- Don't use except for the original purpose.

6. Packaging

• 18kg Tin C/N

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

DAEHEUNG CHEMICAL CO., LTD.

68, Sandan-ro 64beon-gil, Pyeongtaek-si, Gyeonggi-

do, Korea

Telephone +82-2-554-8211, +82-31-668-1424 **Facsimile** +82-2-554-8215, +82-31-668-1425

Website www.dhcbond.co.kr



