

SR 9000

**DAEHEUNG CHEMICAL**

Electrical·electronic silicone sealant

SR 9000 is an electrical & electronic RTV silicone sealant which is one component alkoxy type. This is perfectly designed for adhesion of the electrical & electronic parts required to be high temperature of the electronic device. In addition, the quality is guaranteed by the certification UL 94V-0.

1. Uses

- Adhesion for the parts of electrical & electronic
- Sealing for high temperature applications
(e.g. power supply, home electrical appliances, communications equipment)
- Protection of the parts of equipment in impact and vibration
- Adhesion for general materials such as metal, glass and etc.

2. Characteristics

- UL Flammability Classification : UL 94V-0, UL File No. E239734
- Superb electronic properties
- Easy workability : Non-solvent type, Non-flowable and Non-odor type with one component type
- Excellent weather resistance
- Can be used for most of materials without primer
- Application temperature : -50 ~200°C

3. Physical properties

Properties	Value
Main component	Silicone polymer
Curing system	Alkoxy curing
Appearance	Soft paste
Color	Black, White, Red
Specific gravity	1.45 ~ 1.50
Skin over time	Max.30min(23℃, 50% RH)
Full curing time	72hr(3mm / 23℃, 50% RH)
Hardness	50 ~ 60(Shore A)
Tensile strength	Min. 1.5N/mm ² (ASTM D412)
Dielectric Strength	25KV/mm(ASTM D149)
Shelf life	1year in unbroken package under dry and cool condition(5~25℃)

4. How to use

- **Clean and dry**

Remove oil, dust, impurities that is obstructed the sealant adhesion.

- **Sealing**

After cutting the nozzle of instrument properly in joint width, insert the nozzle in the top of cartridge deeply and then insert the sealant in the joint part slowly.

- **Curing**

After application, please cure it fully not to be shocked a lot.

5. Caution

- The cartridge should not be exposed to direct sunlight & shall be kept in a cool and dry place.
- Use with adequate ventilation and avoid prolonged breathing of vapors.
- Prolonged or repeated skin contact might cause irritation.
- In the event of eye contact wash thoroughly with water and consult a physician immediately.
- Don't use except for the original purpose.
- Don't use to mix with hot-melt.

6. Packaging

- 300ml cartridge
- 2400ml cartridge

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

DAEHEUNG CHEMICAL CO., LTD.

430-8 Mogokdong, Pyongtaeksi, Gyeonggi-do, Korea

Telephone +82-2-554-8211, +82-31-663-5251

Facsimile +82-2-554-8215, +82-31-664-3361

Website www.dhcbond.com



DAEHEUNG CHEMICAL