SR 708



Silicone sealant for polycarbonate

DAEHEUNG CHEMICAL

SR 708 is a silicon RTV product for construction, mainly composed of silicone polymer. It has excellent adhesion, durability and weatherability.

It is silicone sealant for polycarbonate & exterior panel.

1. Uses

- Head light lamp sealing
- Sealing of Curtain wall panel joint
- Sealing of exterior metal panels
- Sealing of window, door and door frame
- Adhesion of lexan P.C , metal, plastic, glass, etc

2. Characteristics

- Easy gun-workability at low 4℃ and high 50℃ temperature.
- Most of the materials used without primer (lexan, metal, glass, plastic, etc)
- Excellent weatherability and chemical resistance

3. Physical properties

Properties	Value
Main component	Silicone polymer
Curing system	Moisture curing
Curing type	Oxime
Appearance	Soft paste
Color	Gray, Green, Clear (order made color)
Specific gravity	1.35~1.40(Clear:1.00~1.04)
Tack free time	Max. 60min (23℃, 50% RH)
Curing full time	72hrs(3mm/ 23℃, 50% RH)
Hardness	25~35 (shore A)
Tensile strength	Min. 1.2N/mm ² (ASTM D412)
Elongation at break	Min. 400%(ASTM D412)
Temperature resistance	-48℃~120℃
Shelf life	1 year in unbroken package under dry and cool condition(5~25℃)

4. How to use

Joint

Check the joint that is considered the seal and repair of the construction materials that draw the plan.

Clean and dry

Clean and remove oil, dust, impurities on surface..

Masking tape

Use masking tape to protect adjacent surfaces.

Back-Up material installation

Back-up material is the polyethylene foam or polyurethane foam .

Primer

Primer can be used only when it is necessary. It can also be used to increase, its supplementary of adhesive strength if a sealant can't get an adhesive strength.

Sealant caulking

Apply positive pressure adequate to properly fill and seal the joint width.

Tooling

Shave the surface of the sealant in same angel by the rubber knife or scoop.

Masking tape & Sealant cleaning

When the tooling is over, just remove the masking tape.

Excess sealant should be cleaned from glass, metal, plastic surfaces while still uncured.

If it is cured, please use the knife.

5. Caution

- The cartridge should not be exposed to direct sunlight & shall be kept in a cool and dry place.
- Use with adequate ventilation and avoid prolonged breathing of vapors.
- Prolonged or repeated skin contact might cause irritation.
- In the event of eye contact wash thoroughly with water and consult a physician immediately.
- Don't use except for the original purpose.
- Don't use to mix with hot-melt.
- Don't use double-layer glass, fishbowl, professional SPEC.

6. Packaging

300ml cartridge

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

DAEHEUNG CHEMICAL CO., LTD.

 $430\text{-}8\ \mathsf{Mogokdong},\ \mathsf{Pyongtaeksi},\ \mathsf{Gyeonggido},\ \mathsf{Korea}$

Telephone +82-2-554-8211, +82-31-663-5251

Facsimile +82-2-554-8215, +82-31-664-3361

Website www.dhcbond.com

